

Product Information & Specifications

917 Crosby Avenue
Sycamore, Illinois 60178-1394
Phone: 815-895-9101 or 800-435-4482
Fax: 815-895-8475 or 800-343-4258

Product: **SPRUCE^R PRIMERS**
98-15 Light Gray
98-16 Black
98-26 Red Iron Oxide

General Description

A specially formulated undercoating that is economically priced and prevents rust, while enhancing the performance of the finish coat.

Suggested Uses:

Most any bare wood and metal surface

Tools

Toys

Railings

Mailboxes

Cars

Construction equipment

Tractors

Benefits:

Fast dry

Sealing & filling properties

Sandable

Reduced over-spray

Improves finish coat adhesion

Protects against rust and corrosion

Rust inhibitive

Additional Info:

Can be used with lacquer, alkyd enamel and acrylic finish coats.

For better adhesion, sand lightly with fine sandpaper or steel wool.

Several light coats rather than one heavy coat is recommended. Any Spruce enamels or lacquers are recommended as a finish coat.

SPRUCE PRIMERS
TECHNICAL INFORMATION

CONTAINER:	16 FLUID OUNCE AEROSOL CAN
LABEL WEIGHT:	12.0 OUNCES (340 GRAMS)
PROPELLANT:	PROPANE N-BUTANE
CAN PRESSURE:	40 PSI @ 70 ⁰ F
FLAMMABILITY:	CLASSIFIED AS "EXTREMELY FLAMMABLE"
FLASH POINT:	-4 ⁰ F
% SOLIDS:	APPROXIMATELY 22%
DRY TIME:	SET TO TOUCH - 5 MINUTES TACK FREE - 20 MINUTES DRY TO RECOAT- 20 MINUTES
VOC (%):	@52%, CANNOT EXCEED 60.0%
MIR VALUE:	@1.12, CANNOT EXCEED 1.20
GLOSS:	FLAT
CHEMICAL RESISTANCE:	GOOD
ADHESION:	EXCELLENT
DURABILITY:	EXCELLENT
APPLICATION TEMPERATURE:	FOR BEST RESULTS 50-90 ⁰ F
HEAT RESISTANCE:	300 ⁰ F (120 ⁰ C)
RESIN SYSTEM:	PHENOLIC
ABRASION RESISTANCE:	GOOD
FLEXIBILITY:	1/4" MANDREL