



UP0711

FLYWEIGHT – Super Lightweight Body Filler

Description	<p>FLYWEIGHT polyester filler is a two component paste used for the filling of holes and imperfections in most substrates.</p> <p>FLYWEIGHT has been specially formulated for the professional using the latest technology in lightweight body fillers, and it combines excellent filling properties together with the easiest sanding of all the U-POL fillers.</p>
Surface preparation & instructions for use	<p>FLYWEIGHT polyester filler can be used on the following surfaces:-</p> <ul style="list-style-type: none">• Bare metal – e.g. Steel, degrease and abrade with P80 paper.• Original paint surfaces (with the exception of thermoplastic acrylics) degrease and abrade with P180 grit paper.• GRP degrease and abrade with P80 grit paper.
Health and Safety Statement	<p><u>FOR PROFESSIONAL USE ONLY.</u> Read full instructions before use.</p> <p>IMPORTANT: This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at WWW.U-POL.COM.</p> <p>U-POL disclaim any liability where the user does not wear the recommended personal protective equipment</p>
Mixing Ratio	<p>100 parts by weight FLYWEIGHT polyester filler, 2 parts by weight U-POL hardener for polyester filler.</p> <p>The exact mixing ratio is not critical, although over or under catalyzation may affect the gel time. Do not greatly over catalyze the paste as this will not significantly speed up the gel time and could lead to bleed through and bleaching problems when over-painting later. Staining may also occur where too little hardener is used.</p>
Pot life	<p>Once mixed, 4-5 mins. at 68°F with 2% hardener.</p>
Tools	<p>Mixing board, filler knife, plastic or rubber spatula</p>
Drying Time	<p>Sandable after 15 mins. at 68°F. IMPORTANT – This fillers is very easy to sand and therefore recommend that nothing coarser or lower than P80 paper is used.</p>
Over painting	<p>FLYWEIGHT polyester filler can be over-painted with most paint systems including 2K.</p>

USA U-POL Representative - Sanders and Associates Inc. 1263 Route 31 South, Lebanon, NJ 08833
Tel: (908) 730 8858 or (800) 340 7824 Fax: (908) 730 6621 or (800) 787 5150
E-mail: sales-us@u-pol.com Website: WWW.U-POL.COM

Issue 9/2007