

5 STAR ADVANTAGE® AUTOBODY PRODUCTS

TECHNICAL DATA INFORMATION

DATED: MAY 2020

PRODUCT NUMBER

#3532 Trim Paint – Gloss Black (Aerosol)	15oz. 6/cs
#3533 Trim Paint – Flat Black (Aerosol)	15oz. 6/cs
#3534 Trim Paint – Semi-Gloss Black (Aerosol)	15oz. 6cs

DESCRIPTION:

5 STAR ADVANTAGE's Trim paint is formulated using an acrylic resin that resists fading from ultraviolet light and degradation from chemicals. Spray like a professional without the equipment, prep time, cleanup, or waste. Several light coats produce a better finish than one heavy coat. A heavy coat applied over an enamel may cause lifting. Bare surfaces or rusted metal surfaces should first be primed with the 5 STAR ADVANTAGE #3525 Sandable Primer.

FEATURES:

Large Fan Spray Head
Dry to the touch in 20 mins.
Resists fading from UV light & chemicals

SUGGESTED USES:

Body Panels Engine Parts
Metal Structures Aviation Parts Heavy Machinery

DIRECTIONS:

1. Surface must be clean, dry and free of rust before painting. Protect surrounding areas from spray mist. For best results, use when can is between 50°F and 90°F (10°C and 32°C).
2. Shake can at least one minute after rattle is heard and occasionally during use.
3. Spray surface with steady even strokes at a distance of 8 to 10 inches (20 to 25cm). Several light coats give a better finish than one heavy coat.
4. If clogging develops, turn sprayhead 1/4 turn or remove and clean sprayhead slot. Do not stick pin or other objects into can opening. With can and sprayhead pointed away from you, reinsert sprayhead with a gentle twisting motion.
5. To clear sprayhead for future use, turn can upside down and spray for 3 seconds. Completely empty cans may be recycled or disposed of with regular trash. Dispose of partially empty cans responsibly. DO NOT incinerate or compact.

Dry Time*:

To touch 5 minutes

To topcoat 15 minutes

*At 72° F, 50% humidity, 1.5 mil thickness

Curing/Recoat time is extended with multiple coats and excessively thick coats

Gloss*:

High Gloss, >80

Flat, <5

Semi-Gloss, 25-35

*as measured on a 60° gloss meter

PROPERTIES:

Coverage	Up to 18 square feet
Cleanup	Paint/lacquer thinner
Flammability	Extremely Flammable
Flash point	-4F
Specific Gravity	0.78
Solids Content	7%
HAPs content	25%
Storage Temperature	40-100F
Application Temperature	50-90F
Abrasion Resistance	Fair
MIR value	Non-flats <0.95 Flat <0.80
Heat Resistance	250F continuous
Resin System	Acrylic lacquer
Shelf life	Guaranteed for 2 years

Packaging:

Cans per case 6

Shipping Classification Consumer Commodity

ORM-D, UN 1950

Hazard Class 2.1

SAFETY INFORMATION - FOR INDUSTRY USE ONLY

DANGER EXTREMELY FLAMMABLE LIQUID AND VAPOR.
VAPORS MAY CAUSE FLASH FIRE. CONTENTS UNDER PRESSURE.
VAPOR HARMFUL. See other cautions on back panel of label.

KEEP OUT OF REACH OF CHILDREN.

WARNING: Cancer and Reproductive Harm

www.P65Warnings.ca.gov.

AVERTISSEMENT: Cancer et Harm Reproductive

www.P65Warnings.ca.gov

ADVERTENCIA: Cáncer y Daños Reproductivos

www.P65Warnings.ca.gov

For Chemical Emergencies/Pour les urgences chimiques

Para Emergencias Químicas

Contact CHEMTREC (day or night) at 1-800-424-9300

www.5starxtreme.com / www.advantagerefinish.com

Manufactured in U.S.A (Manufactured for - ABI/Autobody Brands
International a division of IAMG/International Autobody Marketing Group)
1505 N. Hayden Rd. Ste. 111, Scottsdale, AZ 85257
1-87-REFINISH

Distributed in Canada by: ABI (Autobody Brands International)
A division of IAMG/International Autobody Marketing Group
1368 United Blvd., Unit 102, Coquitlam, BC V3K 6Y2, Canada