



**FINISHING:**

1. When material has cured, in approximately 15 minutes, sand with 80-120 grit sandpaper.
2. Finish sand with 180-240 grit.

**TOPCOATING:**

May be topcoated with polyester, 2K urethane or 1K primer. Refer to paint manufacturer's instructions for topcoat application.

**SPECIAL NOTES:**

May be thinned with SUPER CHARGER™.

**TECHNICAL INFORMATION:**

Appearance as Packaged:  
VOC:

Silver-Gray  
205 g/l

Weight Per Pouch (Density):  
Maximum Recommended Thickness (Sanded):  
Gel Time @ 77° F:  
Sanding Time @ 77° F:  
Catalyst Required:  
Tack Free Time:

Applied: 0.8 g/l  
.56 pounds (Average)  
1/4"  
3.5-4.5 minutes  
15 minutes  
Benzoyl Peroxide  
10-15 minutes

**ASSOCIATED SDS:** Filler: *"Metal Grip Filler 77706"*

Hardener: *"Cream Hardener"*

**HEALTH & SAFETY:**

Read all warnings, first aid, and safety for all components before using. Keep out of reach of children and animals. Protect hands with impervious rubber gloves. Wear face, skin and eye protection. When sanding, we recommend the use of a respiratory covering device to protect from dust (MSA mask P/N 459029 with MSA cartridge 464029 or equivalent). When using power equipment, refer to power tool manufacturer's recommendations for safety equipment. USC products are for industrial use by trained professionals only.

**Emergency Medical or Spill Control Information:**

In U.S. and Canada call CHEMTREC at 1-800-424-9300